

Technical data sheet.

Modellhartgips P3/K

Product description

Modellhartgips P3/K is a low-expansion model hard stone plaster with very high strength values. It is particularly suited for the production of accurate-to-dimension equipment and models.

Information

This technical data sheet is intended to give advice to the best of our knowledge; it replaces any previous technical data sheets. The contents of this technical data sheet are not legally binding.

> Technical data and specifications

Gypsum/ water	2.27 kg/l
Water-gypsum factor	0.44
Slump flow	21 cm
Setting times	
Initial setting time	approx. 9 min
Final setting time	approx. 18 min
Ball indentation hardness	90 N/mm ²
Linear expansion	0.12 %

For further information

please contact:

CASEA GmbH
Pontelstraße 3
99755 Ellrich
Germany
P +49 36332 89-100
F +49 36332 89-202
info@casea-gips.de
casea-gips.de

A company of the
REMONDIS Group

> Logistics and safety notes

Commercial form	bag, big bag and bulk
Shelf life	given dry storage, it can be stored for at least 6 months
Safety notes	see safety data sheet no specific hazards arising from Modellhartgips P3/K